

SAFETY

1. Always place wet floor/hazard signs at all entrances.
2. Allow approximately 1 hour drying time after the final coat of finish before allowing foot traffic.
3. Remember to use proper mopping procedures and keep your back upright and straight to avoid fatigue.



Use proper posture to avoid fatigue.

“How To” Pamphlets In This Admiral/Beach Chemical Series

1. How to care for floor pads, mops, and buckets
2. How to wet mop
3. How to strip a floor
4. How to finish a floor
5. How to spray buff a floor
6. How to shower scrub and recoat a floor
7. How to buff/polish floors
8. How to finish (wax) floors
9. Dilution ratio chart

BEACH CHEMICAL & PAPER CO.

1356 London Bridge Road
Virginia Beach, VA 23453

757-427-2002
757-430-1663
info@beachchemical.com

BEACH CHEMICAL & PAPER CO.

HOW TO FINISH (WAX) FLOORS



A Buyer's Choice for Quality,
Service, and Education

757-427-2002

HOW TO FINISH (WAX) FLOORS



Purpose To provide a protective coating to floor surface which improves the floor's appearance and makes it easier to maintain.

Supplies and Equipment


1 bucket on a dolly or cart with casters
1 wringer
Plastic can liners to fit buckets
Floor hazard signs
Candy striped blue finish mop head
Floor finish

Procedure

- 1) To prepare the area to be finished:
 - a) follow the floor stripping procedure in the "ADMIRAL" pamphlet, "How to strip floors"
 - b) allow floor to dry completely after stripping and rinsing. Dust mop to remove any foreign material or lint.
 - c) move supplies into the area to be finished.
 - d) totally block off the area to be finished by using floor hazard signs, trash cans, or any method to avoid foot traffic during the finishing operation.
 - e) line the bucket with a can liner. Add the finish 1 gallon at a time.
 - f) dip the finish mop head in the finish until thoroughly saturated and wring until moderately dry.
 - g) outline the baseboard edge with finish. Fill the center using a figure eight motion. Re-wet the mop as it begins to feel heavy and continue in the same manner,

working areas approximately 10'x10'.

(figure 8)



h) allow to dry completely. Approximately 20 to 30 minutes.

i) apply several more coats in the same manner except stay 6" to 12" away from the baseboard.

j) allow the floor to dry "cure" for 24 to 48 hours before buffing.

k)rinse mop bucket and wringer with clear water. Store mop head in can liner tightly sealed for next use. Do not rinse.

BEACH CHEMICAL & PAPER CO.

1356 London Bridge Road
Virginia Beach, VA 23453

757-427-2002
757-430-1663
info@beachchemical.com